



REQUIREMENTS FOR CONCRETE COLLARS:

1. CONCRETE: 3/4", 7 SACK, 4000 PSI AT 28 DAYS, 2" TO 4" SLUMP, 4-7% AIR.
2. COLLAR TO BE FORMED AND UNIFORMLY ROUND OR SQUARE.
3. SMOOTH BROOMED FINISH REQUIRED.
4. APPLY CONCRETE CURING COMPOUND.
5. PROTECT FROM TRAFFIC FOR 4 DAYS MIN.

MONUMENT BOX DETAIL

N.T.S.

REVISION	DATE	CITY OF UNION OREGON	STANDARD STREET DETAILS MONUMENT BOX DETAIL	FIGURE R13